


SELF BONDABLE ROUND ALUMINIUM



HIGH TEMPERATURE	H180 TERMO	H180 TERMO
Thermal class	180°C	180°C
Nature of the isolation	Base Coat: Polyesterimide Top Coat: Alyphatic Polyamide	Base Coat: Polyesterimide Top Coat: Aromatic Polyamide
Diameter	Φ 0.315 - 2.00mm	Φ 0.315 - 2.00mm
Grade	G-1B and G-2B	G-1B and G-2B
Colour	Natural	Natural
Bonding temperature	170°C	210°C
Resoftening temperature	155°C	190°C
Breakdown voltage	≥ 1.5 x IEC	≥ 1.5 x IEC
Heat shock	> 175°C	> 175°C
Solderability	n.a.	n.a.
Cut through	≥ 300	≥ 300
Standard	IEC-851 (Testing methods)	IEC-851 (Testing methods)
Certifications	ISO TS 16949 ISO 9001:2000	ISO TS 16949 ISO 9001:2000
Description	Al H180 TERMO "Diameter" G-"Grade"	Al H180 TERMO "Diameter" G-"Grade"